

3M Scotchcast™



<p>RoHS 2002/95/EC REACH 1907/2007/EC</p>

Electrical Insulating Resin 1402FR

Product Description

3M™ Scotchcast™ Resin 1402FR is a halogen free, flame retardant, two component polyurethane resin for room temperature curing. The resin has been designed for flame retardant and chemical resistant properties as well as electrical insulation and mechanical protection of electrical cable joints.

The 1402FR resin is classified as MIW (medium voltage insulation water curable) according Cenelec HD 631.1 S2 Standard.

Once cured, the resin provides impact resistance and durability against moisture, hydro carbons and atmospheric corrosion.

Continuous operating temperature of installed product; -40°C to + 110°C

Application

Electrical insulation and mechanical protection of low and medium voltage electrical joints installed for indoor and outdoor, underground and submerged applications in conditions where flame retardancy and/or resistance to chemicals such as hydro carbons is required.

Features

- Flame retardant
- Halogen Free
- Chemical resistant
- Good adhesion to metals and different plastics
- Hydrophobic behaviour during curing
- Excellent hydrolytic stability
- Available with Closed Mix and Pour Delivery System
- Low exothermic reaction temperature

Process Figures

Mixing Ratio (pbw)	A : B	100 : 21
Pot Life	At 5 °C	35min
	At 23°C	20min
	At 40°C	8min

Typical Properties

Note: This data is not to be used for specifications.

Values listed are typical and should not be considered minimum or maximum.

Property	Value	Specification
Part A		
Density	1,60 g/cm ³	ISO 3675
Viscosity 23°C	10.000 mPas	EN ISO 2555
Part B		
Density	1,23 g/cm ³	ISO 3675
Viscosity 23°C	140 mPas	EN ISO 2555
Part A&B (mixed)		
Density	1,57 g/cm ³	ISO 3675
Viscosity 23°C	2.500 mPas	EN ISO 2555
Exothermic Reaction Temp 40°C	65 °C	HD 631.1 S2
Hydrophobic Behaviour	Passed	HD 631.1 S2
Volume Shrinkage	3,0 %	EN ISO 3521
Part A&B (cured*)		
Mechanical properties		
Hardness Shore D	75	EN ISO 868
Tensile Strength	25 MPa	EN ISO 527
Elongation at Break	2 %	EN ISO 527
Impact Strength (without notch)	>5 KJ/m ²	EN ISO 179
Electrical properties		
Volume resistivity		
at 23 °C	8,0E+14 Ωcm	IEC 60250
at 80 °C	2,5E+11 Ωcm	
Dielectric Strength		
at 23 °C	>20 kV/mm	EN 60243-1
at 80 °C	>20 kV/mm	
Dissipation factor		
at 23 °C	<0,04	IEC 60250
at 80 °C	<0,13	
Dielectric constant		
at 23 °C	<6	IEC 60250
at 80 °C	<8	
Electrical Properties after dry ageing		
Volume resistivity		
at 23 °C	> 1,0E+14 Ωcm	IEC 60250
Dielectric Strength		
at 23 °C	> 20 kV/mm	EN 60243-1
Dielectric constant		
at 23°C	<6	IEC 60250
Electrical Properties after wet ageing		
Volume resistivity		
at 23 °C	> 1,0E+14 Ωcm	IEC 60250
Dielectric Strength		
at 23 °C	> 20 kV/mm	EN 60243-1
Dielectric constant		
at 23 °C	<6	IEC 60250

Flame retardant properties

Flammability	V0 (3mm)	UL94
Content of halogen	<0,5 %	EN 5067-2-1
Conductivity of smoke gas	<10 μ S/mm	EN 5067-2-2
Acidity of smoke gas	>4,3	EN 5067-2-2

Chemical resistance

Unleaded petrol (Super 95)	<4,0 %	EN 60455-2
Diesel fuel	<0,05 %	EN 60455-2
Insulating Oil	<0,10 %	EN 60455-2
Hydraulic Oil	<0,10 %	EN 60455-2
Salt solution 10%	<0,30 %	EN 60455-2

*curing and aging cycles according to Cenelec HD631.1 S2

Usage Information

The resin will be supplied in two-chamber plastic pouches with peelable barrier in the correct stoichiometric proportion, ensuring the correct mixing ratio for applying the resin. This packaging includes a Closed Mix and Pour Delivery System. The integrated pouring spout is opened while attaching the mixed resin bag to the housing of the joint, or by using the supplied opener.

For the 7.18 Litre Mix-pack version of this product, the resin will be supplied in separate cans for component parts A & B in the correct stoichiometric proportion, ensuring the correct mixing ratio when the cans are mixed together. The Mix-pack also includes protective gloves, and a mixing spatula, along with instructions.

For other information, relevant for the usage of the resin, like Gel-Time, Pot-Life, viscosity, density etc. please see above the typical properties.

Storage

3M™ Scotchcast™ Resin 1402FR has a shelf life of at least 36 months when stored between 10°C and 40°C with a humidity level <75% in the originally sealed bag.

The shelf life of the 7.18 Litre Mix-pack version is 12 months, due to the alternative packaging and larger volume. The expiration date of each product appears on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, it is the responsibility of the user to determine applicability of the resin.

Safety and Handling

3M provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, storage, use and disposal information. 3M strongly encourages its customers to review the MSDS on its products prior to their use.

Product Stewardship

3M has a fundamental concern for all who make, distribute and use its products, and for the environment in which we live. This concern is the basis of our philosophy and policies by which we assess the health and environmental information on our products and then take the appropriate steps to protect employee, the public health and the environment.

Customer Notice

3M encourages its customers and potential users of 3M products to review their applications for such products from the standpoint of human health and environmental quality. To help ensure that 3M products are not used in ways for which they were not intended or tested. 3M personnel are available to assist customers in dealing with ecological and product safety considerations. Your 3M sales representative can arrange for the proper contacts.

Regulatory Status

3M™ Scotchcast™ Resin 1402FR is in compliance with all European directives and regulations, relevant for this product.

The 1402FR Resin is in compliance to EU directive 2002/95/EC (RoHS) and EU regulation 1907/2007/EC (REACH)

3M and Scotchcast are trademarks of 3M Company

Important Notice

All statements, technical information and recommendations related to the Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized office of the Seller.

The statements contained herein are made in lieu of all warranties, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY; INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY; FOR ANY INJURY OR FOR ANY DIRECT; INDIRECT; INCIDENTAL OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS.

Electrical Markets Division

3M United Kingdom PLC

Sales Office

PO Box 393

Bedford MK41 0YE

Telephone: 0870 609 4639

Fax: 01234 229 433

3M Ireland Ltd

Sales Office

The Iveagh Building, The Park,

Carrickmines, Dublin 18, Ireland

Telephone: (01) 800 812 732

Fax: 353 1 280 3509

3M United Kingdom PLC

Head Office

3M Centre, Cain Road

Bracknell, Berkshire RG12 8HT

Telephone: 01344 858 000

Fax: 01344 858 758